

### Highlights of Historical Drilling

Hole	from (m)	to (m)	width (m)	Cu (%)	Mo (%)
<b>VP1</b>	21.5	75.5	52	0.82	0.070
<b>VP3*</b>	57.9	188	130.1	0.49	0.010
<b>VP4</b>	112	188	76	0.63	0.010
<b>V2</b>	65.2	106.8	41.7	0.83	0.010
<b>V-3*</b>	42.78	95.63	52.85	0.93	0.007
<b>V4*</b>	6.2	368.1	361.9	0.66	0.018
<b>V5*</b>	6.2	49.9	43.7	1.06	0.010
<b>V6*</b>	74.3	222.7	148.4	0.72	0.010
<b>V-7</b>	13.28	439.78	426.5	0.42	0.012
including	82.7	183.08	100.38	0.53	0.010
<b>V13*</b>	20.4	203.4	183	0.57	0.006
<b>V15**</b>	9.5	292.8	283.29	0.45	0.008
including	54.37	211.97	157.6	0.59	0.007
<b>V-16*</b>	51.93	209.53	157.6	0.54	0.008
including	96.68	148.53	51.85	0.93	0.009
<b>V-18*</b>	48.74	206.48	157.74	0.76	0.019
including	48.74	87.53	38.79	1.45	0.009
<b>V-20**</b>	6.01	252.23	246.22	0.56	0.008
including	11.28	111.93	100.65	0.68	0.007
<b>V-23*</b>	10.23	325.74	315.51	0.59	0.012
including	99.73	145.48	45.75	0.87	0.014
<b>V-26</b>	10.23	153.58	143.35	0.46	0.001
including	10.23	80.38	70.15	0.60	0.002
<b>V-32**</b>	50	358.45	308.45	0.46	0.010
including	306.35	358.45	52.1	0.76	0.013
<b>V-33</b>	8	415.05	407.05	0.41	0.011
including	21.15	337.8	316.65	0.47	0.013
<b>V-34*</b>	30.65	357.9	327.25	0.40	0.009
including	89	173.8	84.8	0.56	0.009
<b>V-47*</b>	56.7	173.85	117.15	0.41	0.012
including	68.8	135	66.2	0.58	0.012
<b>V-58*</b>	59.2	202.25	143.05	0.56	0.022
<b>V-61*</b>	37.2	114.95	77.75	0.51	0.009
including	43	63	20	0.71	0.009

VP: Placer Dome Holes, V: General Minerals Corporation

\* Hole ended in mineralization grading between 0.2 and 0.5% Cu

\*\* Hole ended in mineralization grading more than 0.5% Cu

### Highlights of Los Andes Drilling

Hole ID	From (m)	to (m)	interval (m)	CuT (%)	Mo (%)	CuEq %*
<b>LAV-68</b>	58	250	192	0.46	0.013	0.55
including	58	196	138	0.54	0.010	0.61
including	78	168	90	0.70	0.011	0.77
including	96	122	26	0.99	0.014	1.08
<b>LAV-72</b>	30	250	220	0.52	0.015	0.62
including	32	224	192	0.55	0.014	0.64
including	34	132	98	0.70	0.013	0.79
including	36	80	44	0.85	0.015	0.95
<b>LAV-75</b>	44	356	312	0.39	0.006	NA
including	48	218	170	0.40	0.007	NA
including	48	58	10	0.65	0.007	NA
<b>LAV-73</b>	14.55	250	235.45	0.43	0.012	0.51
including	14.55	94	79.45	0.59	0.013	0.67
including	32	62	30	0.78	0.011	0.86
<b>LAV-77</b>	40	350	310	0.41	0.008	NA
including	40	110	70	0.50	0.013	0.59
<b>LAV-78</b>	27	300	273	0.42	0.009	NA
including	32	62	30	0.58	0.010	0.65
and	102	182	80	0.55	0.010	0.62
including	134	180	46	0.70	0.013	0.78
<b>LAV-81</b>	61.5	386	324.5	0.45	0.011	0.53
including	82	260	178	0.57	0.012	0.65
including	170	260	90	0.60	0.013	0.69
<b>LAV-82</b>	20	250	230	0.41	0.010	0.48
including	20	70	50	0.65	0.014	0.74
including	28	66	38	0.72	0.013	0.81
<b>LAV-83</b>	28	250	222	0.40	0.008	NA
including	164	246	82	0.47	0.012	0.55
including	204	246	42	0.52	0.007	NA
<b>LAV-84</b>	12	250	238	0.43	0.003	NA
including	36	210	174	0.52	0.004	NA
including	140	172	32	0.63	0.007	NA
<b>LAV-85</b>	10	150	140	0.64	0.003	NA
including	10	110	100	0.71	0.003	NA
including	10	54	44	0.86	0.003	NA
<b>LAV-88</b>	41.55	250	208.45	0.57	0.002	NA
including	41.55	116	74.45	0.62	0.002	NA
and	154	242	88	0.61	0.003	NA
<b>LAV-89</b>	27	254	227	0.44	0.024	0.60
including	34	126	92	0.70	0.023	0.85
including	34	100	66	0.81	0.021	0.95
including	36	74	38	0.88	0.021	1.02
<b>LAV-90</b>	8.3	412	403.7	0.42	0.005	na

	including	16	94	78	0.55	0.004	na
	including	32	68	36	0.70	0.003	na
	and	174	412	238	0.46	0.006	na
	including	308	412	104	0.58	0.004	na
	<b>LAV-91</b>	8.8	362	353.2	0.52	0.011	0.59
	including	64	362	298	0.58	0.012	0.66
	including	68	192	124	0.65	0.019	0.78
	including	68	122	54	0.71	0.012	0.79
	<b>LAV-94</b>	44	476	432	0.41	0.006	na
	including	44	142	98	0.50	0.008	na
	including	46	74	28	0.70	0.010	0.77
	<b>LAV-98</b>	110.5	180	69.5	0.54	0.01	0.61
	including	110.5	148	37.5	0.67	0.011	0.74
	including	110.5	130	19.5	0.77	0.01	0.84
	<b>LAV-108</b>	42	260	218	0.57	0.009	na
	including	42	88	46	0.70	0.007	na
	including	42	58	16	0.88	0.010	0.95
	<b>LAV-109</b>	32	230	198	0.41	0.015	0.51
	including	32	100	68	0.50	0.026	0.67
	<b>LAV-112</b>	36	322	286	0.47	0.011	0.54
	including	40	172	132	0.56	0.013	0.65
	including	94	138	44	0.66	0.017	0.77
	including	96	112	16	0.72	0.024	0.88
	<b>LAV-118</b>	74	172	98	0.43	0.015	0.53
	including	90	134	44	0.50	0.013	0.59
	including	124	134	10	0.64	0.010	0.71
	and	294	298	4	0.79	0.004	na
	<b>LAV-120</b>	48	230	183	0.44	0.013	0.53
	including	48	168	120	0.45	0.016	0.56
	including	48	68	20	0.54	0.010	0.61
	and	152	168	16	0.69	0.010	0.76
	<b>LAV-123</b>	36	270	234	0.49	0.010	0.56
	including	258	270	12	0.73	0.006	na
	and	36	108	72	0.56	0.012	0.64
	including	44	82	38	0.60	0.009	na
	including	46	62	16	0.66	0.010	0.73
	<b>LAV-124</b>	194	568	374	0.42	0.019	0.55
	including	238	376	138	0.60	0.016	0.71
	including	264	298	34	0.71	0.015	0.81
	including	286	298	12	0.77	0.013	0.86
	Mo						
	Enrichment	388	462	74	0.27	0.038	0.52
	<b>LAV-125</b>	42.95	300	257.05	0.39	0.011	0.46
	including	42.95	250	207.05	0.41	0.012	0.49
	including	46	66	20	0.79	0.012	0.87
	<b>LAV-126</b>	63.15	258	194.85	0.41	0.020	0.54

including	63.15	114	50.85	0.55	0.030	0.75
including	94	112	18	0.67	0.035	0.90
<b>LAV-131</b>	56.8	266	209.2	0.68	0.014	0.77
including	56.8	186	129.2	0.71	0.014	0.80
including	56.8	102	45.2	0.83	0.016	0.94
and	226	252	26	0.95	0.020	1.08

\*Copper equivalent is calculated for Mo values greater than 0.01% using US\$1.50/lb Cu and US\$10.00/lb Mo according to the formula  $Cu\ eq\% = Cu\% + (Mo\% \times 10.00/1.50)$  and is not adjusted for metallurgical recoveries or net smelter return which remain uncertain and are assumed to be 100%.